

NordBit 30/45

Product data sheet



Property		Unit	Limit		Test method
			min.	max.	
Penetration at 25 °C		0.1 mm	30	45	DIN EN 1426
Softening Point		°C	52	60	DIN EN 1427
Flash Point		°C	240	-	DIN EN ISO 2592
Solubility in toluene		% (m/m)	99.0	-	DIN EN 12592
Fraaß breaking point		°C	-	-5	DIN EN 12593
After influence of heat and air	Retained penetration	%	53	-	DIN EN 12607-1 DIN EN 1426
	Increase of the Softening Point	°C	-	8	DIN EN 12607-1 DIN EN 1427
	Change of mass	% (m/m)	-	0.5	DIN EN 12607-1