

NordBit 40/60

Product data sheet



| Property | | Unit | Limit | | Test method |
|---------------------------------|---------------------------------|---------|-------|------|-------------------------------|
| | | | min. | max. | |
| Penetration at 25 °C | | 0.1 mm | 40 | 60 | DIN EN 1426 |
| Softening Point | | °C | 48 | 56 | DIN EN 1427 |
| Flash Point | | °C | 230 | - | DIN EN ISO 2592 |
| Solubility in toluene | | % (m/m) | 99.0 | - | DIN EN 12592 |
| Fraaß breaking point | | °C | - | -5 | DIN EN 12593 |
| After influence of heat and air | Retained penetration | % | 50 | - | DIN EN 12607-1 DIN EN 1426 |
| | Increase of the Softening Point | °C | - | 9 | DIN EN 12607-1 DIN EN 1427 |
| | Change of mass | % (m/m) | - | 0.5 | DIN EN 12607-1 |