

# NordBit 70/100

## Product data sheet



Property		Unit	Limit		Test method
			min.	max.	
Penetration at 25 °C		0.1 mm	70	100	DIN EN 1426
Softening Point		°C	43	51	DIN EN 1427
Flash Point		°C	230	-	DIN EN ISO 2592
Solubility in toluene		% (m/m)	99.0	-	DIN EN 12592
Fraaß breaking point		°C	-	- 10	DIN EN 12593
After influence of heat and air	Retained penetration	%	46	-	DIN EN 12607-1 DIN EN 1426
	Increase of the Softening Point	°C	-	9	DIN EN 12607-1 DIN EN 1427
	Change of mass	% (m/m)	-	0.8	DIN EN 12607-1

In addition, the requirements of the DIN EN 12591 and the TL Bitumen-StB 07, table 1 apply.