

NordBit PPA

Product data sheet



Property	Unit	Characteristic	Test method
Penetration at 25 °C	0.1 mm	25	DIN EN 1426
Softening Point	°C	55.0	DIN EN 1427
Flash Point	°C	> 300	DIN EN ISO 2592

In addition, the requirements of the DIN EN 12591 and the TL Bitumen-StB 07, table 1 apply.