

NordBit S 124

Product data sheet



Property	Unit	Characteristic	Test method
Softening Point	°C	124.0	DIN EN 1427
Penetration at 25 °C	mm/10	1	DIN EN 1426
Penetration Index (Pfeiffer)	-	2.9	Internal test method (Pfeiffer)