

NordBit S 96

Product data sheet



Property	Unit	Typical	Test method
Penetration at 25 °C	0.1 mm	4	DIN EN 1426
Softening Point (ring and ball method)	°C	97.0	DIN EN 1427
Flash Point (Cleveland)	°C	> 300	DIN EN ISO 2592
Density at 15 °C	%	1060	DIN 51757 method 3