

# NordBit 15/25

Product data sheet



Property		Unit	Limit		Test method
			min.	max.	
Penetration at 25 °C		0.1 mm	15	25	DIN EN 1426
Softening Point		°C	60	76	DIN EN 1427
Flash Point (Cleveland)		°C	245	-	DIN EN ISO 2592
Solubility in toluene		% (m/m)	99.0	-	DIN EN 12592
After influence of heat and air	Retained penetration	%	55	-	DIN EN 12607-1 DIN EN 1426
	Increase of the Softening Point	°C	-	10	DIN EN 12607-1 DIN EN 1427
	Change of mass	% (m/m)	-	0.5	DIN EN 12607-1

In addition, the requirements of the DIN EN 13924-1 apply.