

# NordBit S 110

Product data sheet

---



Property	Unit	Characteristic	Test method
Softening Point	°C	105.0	DIN EN 1427
Penetration at 25 °C	mm/10	3	DIN EN 1426